

Material

42 CR 764

black

cross linking: Metallic oxide

| | | | |
|-----------------------|----------------------|-------------|-------|
| revision index | revision date | page | 1 / 3 |
| 6 | 12/21/2011 | | |

| Physical properties | nominal range | typical values | |
|---|----------------|----------------|-------------------|
| Density DIN EN ISO 1183-1 | 1.37 ±0.02 | 1.37 | g/cm ³ |
| Hardness DIN ISO 7619-1 | 42 ±5 | 42 | Shore |
| Rebound resilience DIN 53512 | --- | 46 | % |
| Modulus 100 %, DIN 53504, S2 | > 0.7 | 1.5 | MPa |
| Tensile strength DIN 53504, S2 | > 12 | 15 | MPa |
| Elongation at break DIN 53504, S2 | > 300 | 400 | % |
| Compression set DIN ISO 815, 22 h, 100 °C | < 35 | 26 | % |
| Temperature range | -40°C to 100°C | | |

Declarations of conformity

This overview is purely informative and does not constitute a declaration of conformity (DoC). Please refer to the actual declaration of conformity (DoC) including the conditions and its validity period.

| | Country | Part | Remark | Expires |
|-------------------|---------|------|---|---------|
| Info ROHS and ELV | | | EU 2000/53 (ELV) including EU 2011/65 and EU2015/863 (ROHS III) | see DoC |

Freudenberg

Freudenberg FST GmbH
 Technology&Innovation
 Material Compliance
 Telefon: -
 Fax: -
 Email: MaterialCompliance@fst.com

Material

42 CR 764

black

cross linking: Metallic oxide

| | | | |
|-----------------------|----------------------|-------------|--------------|
| revision index | revision date | page | 2 / 3 |
| 6 | 12/21/2011 | | |

Tested after ASTM D 2000: M 2 BC 410 A14 B14 EO14 EO34 F17 G21

| | | nominal range | typical values |
|---|-------|----------------------|-----------------------|
| Hardness | Shore | 40 ±5 | 42 |
| Tensile strength | MPa | min. 10 | 12.5 |
| Elongation at break | % | min. 500 | 690 |
| A14 Change after aging in Air 70h/100°C | | | |
| Hardness | Shore | 15 | 1 |
| Tensile strength | % | -15 | -10 |
| Elongation at break | % | -40 | -7 |
| B14 Compression set 22h/100°C | | | |
| | % | 35 | 23 |
| EO14 Change after aging in IRM 901 70h/100°C | | | |
| Hardness | Shore | ±10 | 2 |
| Tensile strength | % | -30 | -18 |
| Elongation at break | % | -30 | -19 |
| Volume | % | -10 to 15 | -3 |
| EO34 Change after aging in IRM 903 70h/100°C | | | |
| Tensile strength | % | -70 | -60 |
| Elongation at break | % | -55 | -50 |
| Volume | % | 120 | 70 |
| F17 Low-temperature resistance after 3 min at -40 °C 3min./-40°C | | | |
| | | pass | |
| G21 Tear Resistance >= 10 MPa 23°C | | | |
| | MPa | 26 | 29 |

The material possess an excellent ozone and weather resistance. The diesel fuel- and mineral oil resistance are sufficient.

The given values are based on a limited number of tests on standard test pieces (2mm sheets) produced in the laboratory. The data from finished parts can deviate from above values depending on the manufactories process and the component geometry.

Freudenberg

Freudenberg FST GmbH
 Technology&Innovation
 Material Compliance
 Telefon: -
 Fax: -
 Email: MaterialCompliance@fst.com

Material

42 CR 764

black

cross linking: Metallic oxide

| revision index | revision date | page |
|----------------|---------------|-------|
| 6 | 12/21/2011 | 3 / 3 |

The data represents our present empirical values. It is incumbent on the person placing the order to examine whether it is suitable for its intended purpose, before using the product. All questions regarding the guarantee of this product are in line with our terms and conditions, inasmuch as statutory provisions do not plan for something else.

Freudenberg

Freudenberg FST GmbH
Technology&Innovation
Material Compliance

Telefon: -

Fax: -

Email: MaterialCompliance@fst.com